

Advanced Materials**Araldite® 2026**

Structural Adhesives

**Araldite® 2026****Two component PU adhesive system****Key properties**

- Bonds well to most thermoplastics, metals and glass
- Flexible
- Transparent - water clear
- Room temperature curing

Description

Araldite® 2026 is a two component, room temperature curing, clear transparent polyurethane adhesive for bonding of selected thermoplastics (e.g. polycarbonate), thermoset composites, and bonding of plastics to metals and glass.

Product data

Properties	2026/A	2026/B	2026 (mixed)
Colour (visual)	transparent	transparent	transparent
Specific gravity	ca 1.1	ca 1.1	ca 1.1
Viscosity (Pas)	10 - 20	7 - 11	ca. 10
Pot Life (100 gm at 25°C)	-	-	3 - 4 minutes

Processing**Pretreatment**

The strength and durability of a bonded joint are dependant on proper pretreatment of the surfaces to be bonded. At the very least, metal joint surfaces should be cleaned with a good degreasing agent such as acetone, iso-propanol (for plastics) or other proprietary degreasing agents in order to remove all traces of oil, grease and dirt. Low grade alcohol, gasoline (petrol) or paint thinners should never be used.

The strongest and most durable metal joints are obtained by either mechanically abrading or chemically etching ("pickling") the degreased surfaces. Abrading should be followed by a second degreasing treatment.

Pretreatment of thermoplastics such as PVC, Polycarbonate, PET and PMMA should be made by degreasing with either Petroleum ether (of boiling point 40 – 60°C) or with iso-propanol. Use of strong solvents such as acetone is not recommended due to the risk of damage to the plastic surface. Light abrasion can improve adhesion on some plastics such as PVC and PMMA but may cause stress cracking of plastics such as Polycarbonate.

Mix ratio	Parts by weight	Parts by volume
Araldite® 2026/A	100	100
Araldite® 2026/B	100	100

Resin and hardener are available in cartridges incorporating mixers and can be applied as ready-to-use adhesive with the aid of the tool recommended by Huntsman Advanced Materials. Working life in the mixing nozzles is ca. 5 minutes.

Application of adhesive

The resin/hardener mix is applied directly or with a spatula, to the pretreated and dry joint surfaces.

A layer of adhesive 0.05 to 0.10 mm thick will normally impart the greatest lap shear strength to the joint.

The joint components should be assembled and clamped as soon as the adhesive has been applied. An even contact pressure throughout the joint area will ensure optimum cure.

Mechanical processing

Specialist firms have developed metering, mixing and spreading equipment that enables the bulk processing of adhesive. We will be pleased to advise customers on the choice of equipment for their particular needs.

Equipment maintenance

All tools should be cleaned before adhesives residues have had time to cure. The removal of cured residues is a difficult and time-consuming operation.

If solvents such as acetone are used for cleaning, operatives should take the appropriate precautions and, in addition, avoid skin and eye contact.

Times to minimum shear strength

Temperature	°C	10	15	23	40	60	100
Cure time to reach	hours	4	2½	1	-	-	-
LSS > 1N/mm ²	minutes	-	-	-	15	6	2
Cure time to reach	hours	60	15	8	4	-	-
LSS > 10N/mm ²	minutes	-	-	-	-	30	12

LSS = Lap shear strength.

Typical cured properties


Unless otherwise stated, the figures given below were all determined by testing standard specimens made by lap-jointing 170 x 25 x 1.5 mm strips of aluminium alloy. The joint area was 12.5 x 25 mm in each case.

The figures were determined with typical production batches using standard testing methods. They are provided solely as technical information and do not constitute a product specification.

Average lap shear strengths of typical metal-to-metal joints (ISO 4587)

Cured for 16 hours at 40°C and tested at 23°C


Pretreatment - Sand blasting



Average lap shear strengths of typical non-metallic joints (ISO 4587)


Cured for 16 hours at 40°C and tested at 23°C

Pretreatment - Lightly abrade and alcohol degrease. (glass – degreased only)



Lap shear strength versus temperature (ISO 4587) (typical average values)

Cure: (a) = 7 days /23°C; (b) = 24 hours/23°C + 30 minutes/80°C



Roller peel test (ISO 4578)

Cured 16 hours/40°C

8.0 N/mm

Elongation at break at 23°C

50%

Tensile strength at 23°C (ISO R527)

18 MPa

E-modulus


200 MPa

Glass transition temperature

ca. 20°C

Lap shear strength versus immersion in various media (typical average values)


Unless otherwise stated, L.S.S. was determined after immersion for 90 days at 23°C




Lap shear strength versus tropical weathering

(40/92, DIN 50015; typical average values) Cure: 16 hours/40°C; Test: at 23°C

On Aluminium – degreased and sandblasted




On Polycarbonate – Isopropanol degreased



Lap shear strength versus heat ageing, Cure: 16 hours/40°C

On Aluminium – degreased and sandblasted

**Thermal cycling**100 cycles of 6 hour duration from -30°C to 70°C: 18 N/mm²**Shear modulus (G') DIN 53345**

-50°C	1GPa
0°C	0.8GPa
20°C	0.6GPa
40°C	0.2GPa
60°C	10MPa

Flexural Properties (ISO 178) Cure 16 hours/ 40°C tested at 23°C

Flexural Strength	5.5 MPa
Flexural Modulus	274.2 MPa

Storage

Araldite® 2026/A and Araldite® 2026/B may be stored at 2-40°C provided the components are stored in sealed containers. The expiry date is indicated on the label. Cartridges should not be stored for long periods after removal from the foil overpack.

**Handling
Precautions****Caution**

Our products are generally quite harmless to handle provided that certain precautions normally taken when handling chemicals are observed. The uncured materials must not, for instance, be allowed to come into contact with food-stuffs or food utensils, and measures should be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The wearing of impervious rubber or plastic gloves will normally be necessary; likewise the use of eye protection. The skin should be thoroughly cleansed at the end of each working period by washing with soap and warm water. The use of solvents is to be avoided. Disposable paper - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. These precautions are described in greater detail in the Material Safety Data sheets for the individual products and should be referred to for fuller information.

Huntsman Advanced Materials
(Switzerland) GmbH
Klybeckstrasse 200
4057 Basel
Switzerland

Tel: +41 (0)61 299 11 11
Fax: +41 (0)61 299 11 12

www.huntsman.com/advanced_materials
Email: advanced_materials@huntsman.com



Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the buyer. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

While all the information and recommendations in this publication are, to the best of our knowledge, information and belief, accurate at the date of publication, NOTHING HEREIN IS TO BE CONSTRUED AS A WARRANTY, EXPRESS OR OTHERWISE. IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO DETERMINE THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE.

The behaviour of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

Araldite is a registered trademark of Huntsman Corporation or an affiliate thereof.

Copyright © 2009 Huntsman Corporation or an affiliate thereof. All rights reserved.