

Huntsman Advanced Materials Americas Inc.  
5121 San Fernando Road West  
Los Angeles, CA 90039  
818.247.6210

Customer Service Hotline: 800.367.8793  
Customer Service Faxline: 517.351.6255  
Technical Inquiries: 800.817.8260



website: [www.araldite.com](http://www.araldite.com)  
e-mail: [adhesives\\_group@huntsman.com](mailto:adhesives_group@huntsman.com)

## Product Data

# ARALDITE<sup>®</sup> AW 136 Resin Hardener HY 5049 EPOXY LAMINATING ADHESIVE

---

**DESCRIPTION:** Araldite AW 136 resin/Hardener HY 5049 epoxy adhesive is a two-part laminating system used for fabricating skis, snowboards and other composite parts. A heat cure is recommended for optimal results.

---

**APPLICATIONS:**

- Ski and snowboard lamination
- Archery limb lamination
- Honeycomb core facings

---

**ADVANTAGES:** Outstanding adhesion to many materials commonly used in the ski industry. Excellent strength under static and dynamic loading. Good environmental resistance to water, ice and tropical conditions.

---

---

<b>TYPICAL PROPERTIES:</b>	<b><u>Araldite AW 136 Resin</u></b>	<b><u>Test Values</u></b>
	Color, ASTM D-695, Visual	Black
	Specific Gravity, g/cc, ASTM D-792	1.39
	Viscosity, cP @ 77°F (25°C), ASTM D-2393	50,000
	<b><u>Hardener HY 5049</u></b>	
	Color, Visual	Amber
	Specific Gravity, g/cc, ASTM D-792	0.93
	Viscosity, cP @ 77°F (25°C), ASTM D-2393	900
	<b><u>Mixed System</u></b>	
	Color, Visual	Black
	Viscosity, cP @ 77°F (25°C), ASTM D-2393	7500
	Gel Time, minutes, ASTM D-2471, (100 gram mass) @ 77°F (25°C)	75

---

<b>CURE SCHEDULE:</b>	<b><u>Temperature</u></b>	<b><u>Minimum Cure Time</u></b>
	140°F (60°C)	60-120 minutes
	176°F (80°C)	30-60 minutes
	212°F (100°C)	15-20 minutes
	248°F (120°C)	10-15 minutes

---

<b>APPLICATION OF ADHESIVE:</b>	A layer of adhesive 0.002 to 0.004-inches (0.05 to 0.10-mm) thick will normally impart the greatest lap shear strength to a joint.
	The joint components should be assembled and clamped as soon as the adhesive has been applied. Even contact throughout surfaces to ensure proper cure.

---

<b>STANDARD LAP TEST:</b>	Unless otherwise stated, the figures given below were all determined by testing standard specimens made up by lap-joint 4-inch x 1-inch x 0.06-inch (10-cm x 2.5-cm x 1.5-mm) strips of degreased and 100-grit abraded aluminum. The joint area was 0.5 x 1 inch (12.5 mm x 2.5 cm) in each case. Samples were cured at 176°F (80°C) for 30 minutes, unless otherwise noted.
---------------------------	--

---

**TYPICAL CURED  
PROPERTIES:**

Tested at 77°F (25°C) unless otherwise noted.  
Not for specification purposes.

Lap Shear Strength, psi (MPa)  
ISO 4578

**Test Values*****Effect of Test Temperature***

Cured at 212°F (100°C) for 15 minutes. Load applied 10 minutes after specimens reach test temperature.

**Test Temperature**

-40°F (-40°C)	2160 (14.9)
-4°F (-20°C)	2450 (16.9)
68°F (20°C)	2590 (17.8)
104°F (40°C)	2690 (18.5)
140°F (60°C)	2980 (20.5)
176°F (80°C)	1580 (10.9)
212°F (100°C)	500 (3.4)

Tropical Exposure

Exposed to 104°F (40°F) and 92% RH.

**Exposure**

Standard - As Prepared	2880 (19.8)
10 days	2520 (17.4)
30 days	2520 (17.4)
60 days	2660 (18.3)
90 days	2380 (16.4)

Water Immersion at 75°F (23°C)

**Exposure**

Standard - As prepared	2880 (19.8)
10 days	2740 (18.9)
30 days	2590 (17.8)
60 days	2450 (16.9)
90 days	2160 (14.9)

Various Substrates

Steel to steel	DIN 53295, tested at 73°F (22°C)	2450 (16.9)
----------------	--	-------------

---

Standard Drum Peel, pli (N/mm)

<b>Material</b>	<b>Failure Mode</b>	
Aluminum/Aluminum	Cohesive	2.2 (0.38)
Ash/Aluminum	Wood	5.1 (0.89)
Ash/Fabric	Glass Fiber	6.3 (1.1)
ABS/Roving Laminate	Glass Fiber	4.5 (.78)
ABS/Aluminum	ABS	12 (2.1)
Aluminum/Roving Laminate	Glass Fiber	4 (0.7)
Polyurethane Core/Aluminum	Core	1.7 (0.29)
Polyurethane Core/Fabric	Glass Fiber	7.4 (1.3)
Aluminum/Fabric	Glass Fiber	10.8 (1.9)
Aluminum/Rubber Sheet/Aluminum	Rubber Sheet	50.7 (8.9)

### TYPICAL PHYSICAL PROPERTIES

Tested at 77°F (25°C) and cured 7 days at 77°F (25°F) unless otherwise noted.

Not for specification purposes.

	<u>Test Values</u>
Hardness, Shore D, ASTM D-2240	82
Ultimate Tensile Strength, psi (MPa), ASTM D-638	5880 (40.5)
Tensile Modulus, psi (MPa), ASTM D-638	585,000 (4034)
Ultimate Flexural Strength, psi (MPa), ASTM D-790	10,000 (68.9)
Flexural Modulus, psi (MPa), ASTM D-790	500,000 (3,448)
Tg per DMA, °F (°C), ASTM D-4065, cured 15 minutes at 212°F (100°C)	158 (70)
Izod Impact, ft lb/in (J/m), ASTM D-256	0.244 (13)
Ultimate Compressive Strength, psi (MPa), ASTM D-695	18,800 (129.6)
Compressive Modulus, psi (MPa), ASTM D-695	298,000 (2,055)

---

**NOTE ON TYPICAL:** These physical properties are reported as typical test values obtained by our test  
**PROPERTIES:** laboratory. If assistance is needed in establishing product specifications, please  
consult with our Quality Control Department.

---

## CAUTION:

Huntsman Advanced Materials Americas Inc. maintains up-to-date Material Safety Data Sheets (MSDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material. Copies of the latest MSDS may be requested by calling our customer service group at 800-367-8793 or emailing your request to [adhesives\\_group@huntsman.com](mailto:adhesives_group@huntsman.com).

## FIRST AID!

Eyes and skin: Flush eyes with water for 15 minutes. Contact a physician if irritation persists. Wash skin thoroughly with soap and water. Remove and wash contaminated clothing before reuse.

Inhalation: Remove subject to fresh air.

Swallowing: Dilute by giving water to drink and contact a physician promptly. Never give anything to drink to an unconscious person.

## KEEP OUT OF REACH OF CHILDREN

## FOR PROFESSIONAL AND INDUSTRIAL USE ONLY

### **IMPORTANT LEGAL NOTICE:**

Sales of a referenced product ("Product") are subject to the general terms and conditions of sale of Huntsman Advanced Materials Americas Inc. ("Huntsman").

**WARRANTY:** Huntsman warrants to the Buyer that the Product will conform to the published specifications for that Product at the time of manufacture, and that the Product will be free from defects in material and workmanship in normal use.

**DISCLAIMER AND LIMITATION OF LIABILITY:** EXCEPT AS SET FORTH ABOVE, SELLER MAKES NO WARRANTY OR REPRESENTATION, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Huntsman cannot control Buyer's application and use of the Product and accepts no responsibility therefore. No statement or recommendation contained in any Product literature may be construed as a representation about the suitability of a Product for the particular application of Buyer or user or as an inducement to infringe any relevant patent. Buyer is responsible to ensure that its intended use of the Product does not infringe any third-party's intellectual property rights. Seller neither assumes, nor authorizes any representative or other person to assume for it, any obligation or liability other than as is expressly set forth herein. UNDER NO CIRCUMSTANCES SHALL HUNTSMAN BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL, SPECIAL OR OTHER INDIRECT DAMAGES AS A RESULT OF A BREACH OF ANY WARRANTY OR THE FAILURE OF A PRODUCT OR ANY CLAIM THAT IS ESSENTIALLY BASED UPON SUCH BREACH OR FAILURE. Any claim by Buyer, whether arising in contract, tort, negligence, breach of warranty, strict liability, or otherwise, related to a Product shall be limited to, and the sole liability of Seller and the sole remedy of Buyer for any claims shall be for, the purchase price of the Product in respect of which such claim is made. The foregoing DISCLAIMER and LIMITATION OF LIABILITY supercedes Buyer's documents.

**WARNING:** Technical data and results are based upon tests under controlled laboratory conditions and must be confirmed by Buyer by testing for its intended conditions of use. The Product has not been tested for, and therefore is not recommended or suitable for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended or likely, or for uses for which implantation within the human body is intended, and Huntsman assumes no liability for any such uses.

© 2004 Huntsman Advanced Materials Americas Inc.  
Araldite is a registered trademark of Huntsman LLC or an affiliate thereof in one or more, but not all, countries.